

Applikations-Info



Produkt Product Prodotto Produit	Voc-konform	Additive		Verarbeitungszeit Pot life Verwerkings tijd Tempo la bazza Temps de traitement	Applikation							Trockenzeit · Dryingtime Droogtijd · Tempo l'essiccazione Hors poussière		
		Härter Hardener Verharder Induratore Durcisseur	Verdüner Thinner Verdunner Diluente Diluant		Spezial-Additive (falls erforderlich) - (if necessary) (indien vereist) - (ove necessario) - (si nécessaire)	Dispersionsgröße nozzle size spiroerprootte ugello - base mm	Druck spray pressure spuitdruk pressione - pression bar	Dispersionsgröße nozzle size spiroerprootte ugello - base mm	Druck spray pressure spuitdruk pressione - pression bar	rolen paintroller spuitdruk dipingers - bobine	streichen brush kwasten penello - pinceau	Auftragmenge pro Arbeitsfläche Coverage per application	staubtrocken dust dry stofdroog fuori polvere hors poussière	schichtbar sandbar schuurbaar resistente al tatto peut être poncé

Wasserbasis · Waterbase · Watergedragen Base d'eau · En phase aqueuse	Füller · Fillers Vulmiddelen Mastici Bouche-porets et apprêts	Duofill 2K-Wasserfüller weiß DF	✓	10 % PWH 3200 (15 % PWH 3200 Vol.)	0 - 10 % H ₂ O	-	3 h	0,33 - 0,38	110 - 130	2,0 - 2,5	1,5 - 3,0	-	-	120 - 200	30 min.	6 h	-
Buntlacke Coloured lacquers Kleurlakken Laccati Peintures	Buntlacke Coloured lacquers Kleurlakken Laccati Peintures	Variocryl® Color 1K/2K-Buntlack	✓	2K: 10 % PWH 3200	0 - 10 % VO o. 0 - 10 % H ₂ O	0 - 5 % STP-F/STP-G	4 h	0,23 - 0,28	110 - 130	1,6 - 1,8	1,5 - 3,0	-	-	100 - 120	40 min.	4 h	12 - 16 h
		Variocryl® Color 2K-PUR-Effektack VCC MB, PGB, Gold	✓	5 % PWH 3200	-	-	-	-	-	-	-	-	-	-	-	-	-

Wasserbasis · Waterbase · Watergedragen Base d'eau · En phase aqueuse	Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Duocryl 2K-Parkettlack DC-P 8, 9	✓	5 % PWH 3500	0 - 10 % H ₂ O	0 - 5 % STP-F/STP-G	2 h	-	-	-	-	✓	✓	80 - 120	40 min.	2 - 3 h	12 - 16 h
Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Duocryl 2K-PUR-Top-Wasserklarlack DC-T 8, 9, 0	✓	20 % PWH 3200	10 - 20 % H ₂ O	0 - 5 % STP-F/STP-G	4 h	0,25 - 0,33	110 - 130	1,8 - 2,0	1,5 - 3,0	✓	✓	80 - 140	30 min.	4 - 5 h	12 - 16 h
		Medicryl 2K-PUR-Wasserklarlack MC 8, 9, 0	✓	-	-	-	-	-	-	-	-	-	✓	✓	100 - 140	30 min.	4 - 5 h

Lösemittelbasis · Solvent-Basis · Oplosmiddelhoudend Base di solvente · En phase solvant	Füller Fillers Vulmiddelen Mastici Bouche-porets et apprêts	Wigranit® 2K-MDF-Isolierfüller weiß WIG-IF	✓	20 % S 8888 (25 % S 8888 Vol.)	-	-	8 h	0,33 - 0,38	110 - 130	2,0 - 2,5	1,5 - 3,0	-	-	200 - 250	20 min.	6 h	-	
																		Wigranit® 2K-PUR-Füller weiß WIG/FILL
Buntlacke Coloured lacquers Kleurlakken Laccati Peintures	Buntlacke Coloured lacquers Kleurlakken Laccati Peintures	Wigranit® Novacolor 2K-PUR-Buntlack WNC/Farbtone	-	10 % PUR 5085 o. TH	0 - 20 % S 9004/S 9029	0 - 10 % MK, 0 - 3 % BS, 0 - 5 % VZ, 0 - 5 % STP-F/STP-F, 1 % AS	8 h	0,23 - 0,28	110 - 130	-	-	-	-	-	120 - 150	30 min.	6 h	12 - 16 h
		Wigranit® Novacolor 2K-PUR-Effektack WNC/MB, PGB, Gold	-	5 % PUR 5085	-	-	-	8 h	-	-	1,6 - 2,0	1,5 - 3,0	-	-	120 - 150	30 min.	6 h	12 - 16 h

Lösemittelbasis · Solvent-Basis · Oplosmiddelhoudend Base di solvente · En phase solvant	Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Crystallit® 2K-Füllgrund CL-F	✓	10 % PUR 5085	0 - 20 % S 9004/S 9029	0 - 3 % BS, 0 - 5 % VZ	8 h	-	-	-	-	-	-	100 - 140	20 min.	1 - 2 h	-
Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Colourit 2K-PUR-Lack, koloriert COL 7, 8, 9, 0	✓	10 % PUR 5085	-	0 - 10 % MK, 0 - 3 % BS, 0 - 5 % VZ, 0 - 5 % STP-G/STP-F, 1 % AS	36 h	-	-	-	-	-	-	90 - 120	20 min.	-	12 - 16 h
		Crystallit® 2K-PUR-Klarlack CL 7, 8, 9, 0	✓	10 % PUR 5085	0 - 20 % S 9004/S 9029	0 - 10 % MK, 0 - 5 % VZ, 0 - 5 % STP-G/STP-F, 1 % AS, 0 - 10 % SB	36 h	-	-	-	-	-	-	-	90 - 120	20 min.	1 - 2 h

Lösemittelbasis · Solvent-Basis · Oplosmiddelhoudend Base di solvente · En phase solvant	Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Duritan® 3K High-Solid Füllgrund DT-F	✓	DT-FDHI:DA2 100:100:2	0 - 5 % S 9004	-	8 h	-	-	1,0 - 1,3	2,0 - 3,0	-	-	80 - 120	10 min. nach der Belichtung after exposure naar belichting dopo l'esposizione	10 min. nach der Belichtung after exposure naar belichting dopo l'esposizione	1 h nach der Belichtung after exposure naar belichting dopo l'esposizione
Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Klarlacke Clear varnishes Blanke lakken Vernici trasparenti Vernis transparents	Duritan® 3K High-Solid Tiefmattlack DT-TM	✓	DT-TM:DH1:DA2 100:50:4	-	-	-	-	-	-	-	-	-	-	-	-	-